

CORR. GLASS	AGGRESSIVENESS OF THE ENVIRONMENT	EXAMPLES OF ENVIRONMENTS	CORROSION RATE OF ZINC	GUIDING DURABILITY OF CHROMATE
0	NONE	INDOOR, DRY	AVERAGE (0-0)µm/YEAR	SALT SPRAY 48 HOURS TO WHITE RUST SALT SPRAY 96 HOURS TO WHITE RUST BLUE YELLOW > 10 YEARS > 10 YEARS
1	INSIGNIFICANT	INDOOR, UNHEATED, WELL VENTILATED	0,5 (0-1)µm/YEAR	½ - 1 YEAR 3 - 5 YEARS
2	MEDIUM		1,5 (1-2)µm/YEAR	3-6 MONTHS 2-3 YEARS
3	HIGH		3 (2-5)µm/YEAR	1-3 MONTHS 1-2 YEARS